IN THE SPECIFICATION

Please amend the paragraph at page 66, lines 22-24, as follows:

As for the mixing machine, there is, for example, a V-type mixer, a ~~Rocking mixer~~ ROCKING MIXER, a ~~Loedige mixer~~ LOEDIGE MIXER, a ~~Nauta mixer~~ NAUTA MIXER, and a ~~Henschel mixer~~ HENSCHEL MIXER.

Please amend the paragraph at page 106, lines 9-27, as follows:

The foregoing materials was mixed with a ~~Henschel mixer~~ HENSCHEL MIXER, to thereby obtain a mixture where water is impregnated in a pigment aggregate. Subsequently, the mixture was kneaded with twin rollers with a surface temperature of 100^{0}C for 45 minutes, then, rolling and cooling are performed, and then, milling is performed with a pulverizer. Thereby, a masterbatch pigment was obtained.

- polyol resin 1 95 parts
- above-described masterbatch 10 parts
- charge control agent (Bontron E-84 manufactured by Orient Chemical Industries) 2 parts
- wax (fatty acid ester wax, melting point 83^{0}C, viscosity 280mPa · s (90^{0}C)) 5 parts

Please amend the paragraph at page 108, line 15, to page 109, line 2as follows:

The foregoing materials was mixed with a ~~Henschel mixer~~ HENSCHEL MIXER, to thereby obtain a mixture where water is impregnated in a pigment aggregate. Subsequently, the mixture was kneaded with twin rollers with a surface temperature of 130^{0}C for 45

minutes, then, rolling and cooling are performed, and then, milling is performed with a pulverizer. Thereby, a masterbatch pigment was obtained.

polyol resin 1	92 parts
· above-described masterbatch	16 parts
· charge control agent (Bontron E-84 manufactured by Orient Chemical Industries)	2 parts
· wax (fatty acid ester wax, melting point 83^{0}C, viscosity 280mPa · s (90^{0}C))	5 parts

Please amend the paragraph at page 110, lines 10-23, as follows:

The foregoing materials were mixed with a ~~Henschel mixer~~ HENSCHEL MIXER, to thereby obtain a mixture where water is impregnated in a pigment aggregate. Subsequently, the mixture was kneaded with twin rollers with a surface temperature of 130^{0}C for 45 minutes, then, rolling and cooling are performed, and then, milling is performed with a pulverizer. Thereby, a masterbatch pigment was obtained.

· polyol resin 1	96 parts
· above-described masterbatch	4 parts
· charge control agent (Bontron E-84 manufactured by Orient Chemical Industries)	2 parts
· wax (fatty acid ester wax, melting point 83^{0}C, viscosity 280mPa · s (90^{0}C))	5 parts

Please amend the paragraph at page 112, lines 3-7, as follows:

By adding the aforementioned inorganic fine particles 1 to 4 of 3.0 wt % to a toner (developer), mixing with a ~~Henschel mixer~~ HENSCHEL MIXER, filtering with a mesh size of 50μm, and removing aggregate material, toner for each color was obtained.